

## High-Efficiency Broadband Anti-Reflective (BBAR) Coating on Zinc Selenide (ZnSe), 3 - 5µm

COATING DATA SHEET

### Application

High-Efficiency Broadband Coating for the 3 - 5µm range gives low reflection and high transmission for use in passive imaging systems. This coating is not intended for high power laser applications.

### Spectral Performance

Transmission when measured through a 3mm thick ZnSe substrate coated on both surfaces with the broadband AR coating.

$T \geq 98.0\%$  average from 3 - 5µm

Reflection from a single surface when coated with the broadband AR coating.

$R \leq 0.5\%$  average from 3 - 5µm

This coating can be modified for similar performance at other wavelengths.

### Environmental Performance

This coating is designed to meet durability requirements of the following MIL Specifications:

Adhesion	MIL-C-48497 MIL-C-675C
Humidity	MIL-C-48497 MIL-C-675C
Moderate Abrasion	MIL-C-48497 MIL-C-675C

